



ALSEY
refractories co.

PRODUCT DATA

EXETER 90P

90% Alumina, dry press firebrick of various sizes

TYPICAL TEST DATA

CHEMICAL ANALYSIS [Wt. % Calcined Basis]

Silica [SiO ₂].	6.0
Aluminum Oxide [Al ₂ O ₃].	90.3
Titanium Dioxide [TiO ₂].	1.0
Iron Oxide [Fe ₂ O ₃].	0.7
Phosphorus Pentoxide [P ₂ O ₅].	1.6
Other Oxides.	0.1
Alkali [Na ₂ O/K ₂ O].	0.2
Calcium Oxide [CaO].	0.1
Total	100.0
Loss on Ignition, 1000°C.	0.0

PHYSICAL PROPERTIES

ASTM C-24

P.C.E.	>40
Service Temperature [max. recommended], °F	3300

ASTM C-133

Modulus of Rupture [MOR], psi	3031
Cold Crush	16578

ASTM C-20

Apparent Porosity, %	17.9
Apparent Specific Gravity, g/cc	3.6
Bulk Density [fired] lb./ft ³	184.8

SDS AVAILABLE UPON REQUEST

The above properties represent average results of typical data produced from standard ASTM test methods on a 9" straight. Specifications should not be considered guaranteed. Alsey Refractories Company makes every effort to ensure consistency in our products; however, properties may vary due to standard statistical manufacturing deviations. Alsey Refractories Company reserves the right to modify this data at any time without prior notice.



Alsey Refractories Company
266 State Route 106 South P O BOX 80
Alsey IL 62610
314.963.7900 | info@alsey.com