



**ALSEY**  
refractories co.

# PRODUCT DATA

MOHITE®

Special Super Duty Firebrick, Alumina dry press firebrick of various sizes for aggressive environments

## TYPICAL TEST DATA

### CHEMICAL ANALYSIS [Wt. % Calcined Basis]

Silica [SiO <sub>2</sub> ]	<52
Aluminum Oxide [Al <sub>2</sub> O <sub>3</sub> ]	>44
Titanium Dioxide [TiO <sub>2</sub> ]	1.5
Iron Oxide [Fe <sub>2</sub> O <sub>3</sub> ]	1.0
Phosphorus Pentoxide [P <sub>2</sub> O <sub>5</sub> ]	0.1
Other Oxides	0.3
Calcium Oxide [CaO]	0.1
Alkali [Na <sub>2</sub> O/K <sub>2</sub> O]	0.2
Total	100.0
Loss on Ignition, 1000°C	0.0

### PHYSICAL PROPERTIES

#### ASTM C-24

P.C.E.	>34
Service Temperature [max. recommended], °F	3205

#### ASTM C-133

Modulus of Rupture [MOR], psi	1616
Cold Crush	7624

#### ASTM C-20

Apparent Porosity, %	14-16
Apparent Specific Gravity, g/cc	2.9
Bulk Density [fired] lb./ft <sup>3</sup>	150.9

#### ASTM C-288

CO Exposure [100 hours]	unaffected
-------------------------	------------

SDS AVAILABLE UPON REQUEST

The above properties represent average results of typical data produced from standard ASTM test methods on a 9" straight. Specifications should not be considered guaranteed. Alsey Refractories Company makes every effort to ensure consistency in our products; however, properties may vary due to standard statistical manufacturing deviations. Alsey Refractories Company reserves the right to modify this data at any time without prior notice.



Alsey Refractories Company  
266 State Route 106 South P O BOX 80  
Alsey IL 62610  
314.963.7900 | info@alsey.com